

# SUPERCRYL MATT FINISH

High Quality, Highly Durable, Water Based Acrylic Paint for Exterior and Interior Walls

## SPECIAL FEATURES

Provides an elegant look and high, long-term durability. Does not peel off or fade. High spreading rate, fast drying, breathing paint, lead and chromates free.

## SUGGESTED USES

Painting interior and exterior plastered walls, concrete and bricks walls.

## TECHNICAL DATA

Product code: 732-2xx (White +4 bases)  
 Color: 1200 colors from Tambour Spectrum fan deck.  
 Gloss: Matt  
 Calculated spreading rate\*: 8-9 sq.m/liter (for white in two coats) 6-7 sq.m/ liter (for shades in two coats).  
 Recommended Thinner: **During application:** water. **For cleaning:** water and soap.  
 Drying Times: **Touch dry\*\*:** 1 hour. **Hard coat:** 3 hours **Dry to recoat:** 3 hours **Completely dry for cleaning and washing:** 7 days after application  
 Shelf life: 24 months  
 Quantity per Pallet:

Package size	Quantity per Pallet
18 liters	36
15 liters	36
10 liters	36
5 liters	80
3 liters	210
1 liter	576

## SURFACE PREPARATION AND PAINT SYSTEM

### Interior Whitewashed Lime surfaces

Remove any loose, flakey, peeling lime or excessively thick layers. Sand with sandpaper to a smooth surface. Clean off dust thoroughly. Apply one coat of **Bonderol Super**. Allow to dry for 4 hours and apply two coats of **Supercryl Matt Finish**.

### Painted Interior Walls

Remove any old, loose and peeling paint. Apply a coat of **Bonderol Super** on peeling paint surfaces. Smooth the surface by applying **Magic Bond** or **Glue Putty 2000** (for interior applications only), apply a coat of **Bonderol Super** over it and allow to dry. Apply 2-3 coats of **Supercryl Matt Finish**. When the old paint coat is whole and cannot be removed, apply 2-3 coats of **Supercryl Matt Finish** directly on it.

### New, Unpainted, Plastered Interior Walls

Smooth the surface lightly using sandpaper. Remove dust and fill holes with **Calcimo X**. To obtain a smooth surface, apply a coat of **Tambourfill** and allow drying for 4 hours. Apply 2-3 coats of **Supercryl Matt Finish**.

### Concrete and Cement Plaster Surfaces

Paint can be applied only after the plaster is completely cured (one month or more after application). Remove dust and apply a first coat of white **Bonding Primer White** diluted by about 30% with Tambour Mineral white spirit. Allow to dry for 24 hours at least. Apply 2-3 coats of **Supercryl Matt Finish**.

## APPLICATION REMARKS

Stir the paint well before application and while painting.

### Apply using a brush/ Roller/ Airless:

Dilute the paint with water for the first coat by 20% - 30% and stir well. Dilute the paint with water for the additional coats by 10%-20%. Apply 2-3 coats, according to the surface type.

## CLEANING AND STORAGE

Clean work tools with soap and water, immediately after use. Pour a thin layer of water on the remaining paint and close the container tightly to prevent air penetration. Store in a roofed and ventilated place.

## CAUTION

Inedible, keep out of reach of children. Use in a well ventilated area only. Do not apply when rain is expected or when temperatures drop below 10°C and relative humidity is over 85%.

## GENERAL COMMENTS

Never mix this material with others when not specifically recommended by us.

Achievement of the best desired results is subject to proper application in strict conformance to our instructions and safety measures. Before application, the user should verify that the product is indeed designed for the intended usage and that the surfaces to be painted are properly prepared, and are suitable for the product's application.

Data presented here is based on our best knowledge and experience. We reserve the right to update and/or alter it without prior notice.

## Notes:

- Washable & scrubbing resistant & heavy-duty
- Water based emulsion paint,
- For indoor & outdoor use
- User & Environment Friendly

\* practical spreading rate can vary, depending on the surface, the application mode, the painter's skill and weather conditions at the site.

Assume approximately 75% of the calculated spreading rate.

\*\* at 25°C and 65% relative humidity.