

GLUE PUTTY 2000

Synthetic Resins Based Filler.

SPECIAL FEATURES

Easily sanded.

SUGGESTED USES

Filling and levelling wood surfaces, plaster, concrete and gypsum walls. For interior use only.

TECHNICAL DATA

Product code: 760-001
 Color: Off-White
 Gloss: Matt
 Calculated spreading rate*: For Smoothing: 800 gram/sq.m (in two coats).
 Recommended Thinner: **For cleaning:** water and soap.
 Drying Times: **Holes filling**:** 2 hours. Levelling: 2-4 hours **Dry to recoat:** 2-4 hours
 Shelf life: 12 months
 Quantity per Pallet:

Package size	Quantity per Pallet
0.5 liter	900
1 liter	576
2.5 liters	160
5 liters	100
18 liters	27

SURFACE PREPARATION AND PAINT SYSTEM

Clean off any dust, grease, dirt and any other foreign matter.

Whitewashed Walls

Apply **Bonderol Super Primer** and **Glue Putty 2000** using a trowel.

Painted Walls

Remove loose paint. Apply a coat of **Bonderol Super Primer** on repaired surfaces.

Apply 1-2 coats of **Glue Putty 2000** using a trowel.

Wood

Apply a coat of **Wood and Wall Oil Sealer** and allow to dry for 24 hours. Apply **Glue Putty 2000** using a trowel. Allow drying to a hard coat and lightly sand the surface between coats and after applying the top coat. Clean off the sanding dust thoroughly prior to application.

APPLICATION REMARKS

Ready to use Putty. Stir the paint well before application and while painting.

CLEANING AND STORAGE

Clean work tools with soap and water, immediately after use. Pour a thin layer of water on the remaining paint and close the container tightly to prevent air penetration. Store in a roofed and ventilated place.

CAUTION

Inedible, keep out of reach of children. Use in a well ventilated area only. Do not apply when rain is expected or when temperatures drop below 10°C and relative humidity is over 85%.

GENERAL COMMENTS

Never mix this material with others when not specifically recommended by us. Achievement of the best desired results is subject to proper application in strict conformance to our instructions and safety measures. Before application, the user should verify that the product is indeed designed for the intended usage and that the surfaces to be painted are properly prepared, and are suitable for the product's application.

Data presented here is based on our best knowledge and experience. We reserve the right to update and/or alter it without prior notice.

* practical spreading rate can vary, depending on the surface, the application mode, the painter's skill and weather conditions at the site.

Assume approximately 75% of the calculated spreading rate.

** at 25°C and 65% relative humidity.