

Joint Compound

American Joint Compound

SPECIAL FEATURES

Most convenient application, fast drying, easy sanding.

SUGGESTED USES

Fill and repair joints of gypsum boards and smooth interior concrete, plastered and other walls.

TECHNICAL DATA

Product code: 725-041

Color: Off-White

Gloss: Matt

Calculated spreading rate*: 1-2 sq.m/kg (in one coat)

Recommended Thinner: **During application:** Water. **For cleaning:** Water and soap.

Drying Times: **Touch dry**:** 2-3 hours. **Hard coat:** 24 hours **Dry to recoat:** 4 hours

Shelf life: 24 months

Quantity per Pallet:

| Package size | Quantity per Pallet |
|--------------|---------------------|
| 8 kg | 100 |
| 25 kg | 27 |
| 28 kg | 27 |

SURFACE PREPARATION AND PAINT SYSTEM

New Unpainted Interior Walls

Apply one coat of **Bonderol Super Primer** directly on the wall, prior to applying the **Joint Compound**. If the intended topcoat of the wall is an acrylic topcoat (**Supercryl**, etc.), you must apply a coat of **Bonderol Super Primer** on the putty.

APPLICATION REMARKS

The putty is ready to use and no additional dilution is required. When needed, mix the putty well and then add small quantities of clear water, to obtain the required texture. For smoothing walls, apply the putty with a spatula, in one thin coat, or several coats, as needed. Ascertain that the thickness of each putty coat shall not exceed 1 mm.

CLEANING AND STORAGE

Clean work tools with water, immediately after use. Pour a thin layer of water on the remaining paint and close the container tightly to prevent air penetration. Store in a roofed and ventilated place.

CAUTION

Inedible, keep out of reach of children. Use in a well ventilated area only. Do not apply when rain is expected or when temperatures drop below 10°C and relative humidity is over 85%.

GENERAL COMMENTS

Never mix this material with others when not specifically recommended by us.

Achievement of the best desired results is subject to proper application in strict conformance to our instructions and safety measures. Before application, the user should verify that the product is indeed designed for the intended usage and that the surfaces to be painted are properly prepared, and are suitable for the product's application.

Data presented here is based on our best knowledge and experience. We reserve the right to update and/or alter it without prior notice.

* practical spreading rate can vary, depending on the surface, the application mode, the painter's skill and weather conditions at the site. Assume approximately 75% of the calculated spreading rate.

** at 25°C and 65% relative humidity.