

TAMBOURFLEX FILLER PUTTY

Acrylic Putty to Repair and Fill Holes and Defects. Especially Suited for Tambourflex System

SPECIAL FEATURES

Flexible. Can be applied up to a 3 cm thickness.

SUGGESTED USES

Fill and repair holes and defects in external walls.

TECHNICAL DATA

Product code: 737-454
 Color: Grayish
 Gloss: Matt
 Recommended Thinner: **During application:** Water. **For cleaning:** Water and soap.
 Drying Times: **Hard coat:** 24 hours **Dry to recoat:** 2-3 hours
 Shelf life: 24 months
 Quantity per Pallet:

Package size	Quantity per Pallet
4 kg	160

SURFACE PREPARATION AND PAINT SYSTEM

Clean the crack, break and/or hole thoroughly and ensure that it is free of dust, grease or any other foreign matter. Apply **Tambourflex Primer** and allow to dry. Apply **Tambourflex Filler Putty** and allow to dry. Do not seal a crack, a break or a hole deeper than 3 cm with one coat.

APPLICATION REMARKS

The paint is ready to use. When needed, dilute with a little water.

CLEANING AND STORAGE

Clean work tools with water, immediately after use. Pour a thin layer of water on the remaining paint and close the container tightly to prevent air penetration. Store in a roofed and ventilated place.

CAUTION

Inedible. Keep out of reach of children. Use in a well ventilated area only. Do not apply when rain is expected or when temperatures drop below 10°C and relative humidity is over 85%.

GENERAL COMMENTS

Never mix this material with others when not specifically recommended by us. Achievement of the best desired results is subject to proper application in strict conformance to our instructions and safety measures. Before application, the user should verify that the product is indeed designed for the intended usage and that the surfaces to be painted are properly prepared, and are suitable for the product's application. Data presented here is based on our best knowledge and experience. We reserve the right to update and/or alter it without prior notice.

* practical spreading rate can vary, depending on the surface, the application mode, the painter's skill and weather conditions at the site.

Assume approximately 75% of the calculated spreading rate. ** at 25°C and 65% relative humidity.