

# Tamgar

## Synthetic, Ready to Use Plaster

### SPECIAL FEATURES

Excellent adhesion to prefabricated/industrialized wall substrate. Good flexibility. Prevents cracking. Fast application.

### SUGGESTED USES

Plastering walls and interior walls in prefabricated/ industrialized construction. Creates a smooth surface that reduces the number of finishing paint coats.

### TECHNICAL DATA

Product code:	755-001	
Color:	Off-White.	
Gloss:	Matt	
Calculated spreading rate*	1.5-2 sq.m/kg (in one coat)	
Recommended Thinner:	<b>During application:</b> water. <b>For cleaning:</b> water.	
Drying Times:	<b>Hard coat:</b> 4 hours <b>Dry to recoat:</b> 4 hours	
Shelf life:	24 months	
Quantity per Pallet:	<b>Package size</b>	<b>Quantity per Pallet</b>
	28 kg	27

### SURFACE PREPARATION AND PAINT SYSTEM

Remove grease residue from the moulds using **Ardrox BC-70** detergent. Remove concrete residue and other materials. Repair holes and defects using **Tamgar**. Smooth immediately using a wide flat trowel. Spray or apply with a trowel, a second coat of **Tamgar**. Smooth immediately using a wide flat trowel. Allow to dry for 4 hours at least between coats.

### APPLICATION REMARKS

Stir the paint well before application and while painting.  
Can be sprayed, using a dedicated spraying device or applied with a wide trowel.

### CLEANING AND STORAGE

Clean work tools with soap and water, immediately after use. Pour a thin layer of water on the remaining paint and close the container tightly to prevent air penetration. Store in a roofed and ventilated place.

### CAUTION

Inedible, keep out of reach of children. Use in a well ventilated area only. Do not apply when rain is expected or when temperatures drop below 10°C and relative humidity is over 85%.

### GENERAL COMMENTS

Never mix this material with others when not specifically recommended by us.  
Achievement of the best desired results is subject to proper application in strict conformance to our instructions and safety measures. Before application, the user should verify that the product is indeed designed for the intended usage and that the surfaces to be painted are properly prepared, and are suitable for the product's application.  
Data presented here is based on our best knowledge and experience. We reserve the right to update and/or alter it without prior notice.

\* practical spreading rate can vary, depending on the surface, the application mode, the painter's skill and weather conditions at the site. Assume approximately 75% of the calculated spreading rate.

\*\* at 25°C and 65% relative humidity.